

C L A I M SREPLACED BY  
ART 34 AMDT

1. Process to prepare a microcrystalline wax and a middle distillate fuel by

(a) hydrocracking/hydroisomerising a Fischer-Tropsch product, wherein weight ratio of compounds having at least 60 or more carbon atoms and compounds having at least 30 carbon atoms in the Fischer-Tropsch product is at least 0.2 and wherein at least 30 wt% of compounds in the Fischer-Tropsch product have at least 30 carbon atoms,

(b) performing one or more distillate separations on the effluent of step (a) to obtain a middle distillate fuel fraction and a microcrystalline wax having an initial boiling point of between 500 and 600 °C.

2. Process according to claim 1, wherein at least 50 wt% of compounds in the Fischer-Tropsch product have at least 30 carbon atoms.

3. Process according to any one of claims 1-2, wherein the weight ratio of compounds having at least 60 or more carbon atoms and compounds having at least 30 carbon atoms in the Fischer-Tropsch product is at least 0.4.

4. Process according to any one of claims 1-3, wherein the conversion in step (a) is between 25 and 70 wt%.

5. Process according to any one of the claims 1-4, wherein the microcrystalline wax as obtained has a congealing point of between 95-120 °C and a PEN at 43 °C as determined by IP 376 of more than 0.8 mm.

6. Process according to claim 5, wherein the PEN at 43 °C is more than 1.0 mm.

7. Process according to any one of claims 1-6, wherein the wax obtained in step (b) is subjected to an

REPLACED BY  
ART 34 AMDT

additional de-oiling step to obtain a wax having an oil content of between 0.1 and 2 wt%.

8. Microcrystalline wax having a congealing point of between 95 and 120 °C and a PEN at 43 °C as determined by IP 376 of more than 0.8 mm.